


Schematic drawing



System 3.3.2

- 1 Concrete deck
- 2 Primer coat
- 3 Mechanical fastening with anchors PC® F
- 4 FOAMGLAS® slabs, bonded with PC® 56
- 5 Primer layer PC® 164 with reinforcing mesh PC® 150, Primer sealer PC® 130
- 6 Primer sealer PC® 130
- 7 Roughcast render PC® 78

FOAMGLAS® product properties

Waterproof – Resistant to vermin – High compressive strength –
Non-combustible – Impervious to water vapour – Dimensionally stable –
Acid resistant – Easily cut to shape – Ecological


Advantages of the FOAMGLAS® system

- **Quality:** Systems with high quality materials. Quality management by systematic site inspections and professional consulting.
- **Cost efficiency:** The high durability preserves maximum value and guarantees minimal maintenance costs.
- **Sustainability:** Optimum insulation and protection against moisture for generations.
- **Safety:** Compact, fully bonded insulation system preventing damages due to condensate and mould. Cellular glass contains no toxic substances and, in case of fire, does not develop fumes or toxic gases.
- **Functionality:** Insulation, vapour and capillary barrier in one single functional layer.

Recommendations for architects

- Normally used: FOAMGLAS® slabs T4+, size 450/600 mm.
- Insulation thickness to meet building regulations or the project-specific U-value requirements. Please also consult our product overview. It contains information on all our products, their field of application and their specific properties.
- **The flatness and the general conditions of the substrate are important criteria when using FOAMGLAS® (see TG1). Please contact our Technical Department to verify the criteria for the substrate.**
- **For a technically correct implementation, relevant standards and guidelines must be observed.**

Solutions for technical details and specification clauses on request. Further proposals and solutions are available any time from our technical consultants. **Updated: November 2010.** We explicitly reserve the right to change the technical specifications. The current values can be found on our website under: www.foamglas.co.uk/building/applications



Soffit insulation in wet rooms with roughcast finish

FOAMGLAS® slabs with cold adhesive PC® 56


System 3.3.2

Installation instructions

- Primer PC® EM or emulsion PC® 56 diluted with 10 parts of water, applied with a roller on the dust-free surface, coverage $\sim 0.3 \text{ l/m}^2$. (1)
- Apply the FOAMGLAS® slabs fully bonded to the substrate with cold adhesive PC® 56, with staggered joints and joints tightly butted and filled with adhesive. Coverage $\sim 3.5\text{--}4.5 \text{ kg/m}^2$, dependent on the thickness of the insulation:
Apply the cold adhesive PC® 56 with a notched trowel (tooth size $\sim 8\text{--}10 \text{ mm}$) on two sides of the slabs (in stacks). Apply cold adhesive to the entire surface of the slab and push diagonally into the open corner. Remove the squeezed-out adhesive with a trowel when slightly hardened. (2/3)
- Mechanical fastening of the FOAMGLAS® slabs (during application) with anchors PC® F, consumption: 4 pieces/ m^2 . (4)
- Remove irregularities of the insulation surface by grinding with a FOAMGLAS® slab or preferably with an emery board. Remove dust from the FOAMGLAS® surface. (5)
- Allow waiting time of ~ 3 days (dependent on ambient temperature and humidity).
- Apply a base coat of PC® 164 with a stainless steel trowel, coverage $\sim 3.5 \text{ kg/m}^2$. Embed the alkali-resistant reinforcing mesh PC® 150 (overlapping joints $\sim 100 \text{ mm}$) flatly and evenly, mesh structure slightly visible. (6)
- Allow waiting time of $\sim 3\text{--}5$ days (dependent on ambient temperature and humidity).
- Apply the primer sealer PC® 130, coverage $\sim 0.15\text{--}0.3 \text{ l/m}^2$.
- Apply the roughcast render PC® 78 with a stainless steel trowel, grading $0.5\text{--}3 \text{ mm}$, coverage dependent on grading. Finish of the surface with a synthetic disc to desired texture.

Recommendations for the contractor

- The build up and tolerances of the substrate must be in accordance with relevant standards and guidelines.
- Substrate and ambient temperature should not be below $+5^\circ \text{C}$.
- Sensitive components provided by other suppliers must be protected against blobs of adhesive.
- **Please contact our technical consultants; they can help you by providing support or on-site assistance free of charge.**



The technical guidelines for the application and the installation of FOAMGLAS® are based on historical experience and general site practice. They do not reflect individual examples. We therefore assume no liability as to the completeness and the suitability for a specific project. Furthermore, our liability and responsibility are subject to our general conditions of sale which are not extended either by this technical data sheet nor by the consulting of our technical sales representatives.

**Pittsburgh Corning
(United Kingdom) Limited**
 63 Milford Road, Reading
 Berkshire RG1 8LG
 Phone +44 (0)118 950 0655
 Fax +44 (0)118 950 9019
 info@foamglas.co.uk